

Central Park

Style	12mm Laminate
Construction	Laminate Flooring
Classification	NALFA LF-01-2019 (Light Commercial)
Total Thickness	1/2" (12 mm)
Edge Treatment	Micro-bevel
Size	7 9/16"W x 50 1/2"L (192.02 x 1,282.7mm)
Colors	6
Packaging	21.22 ft ² (1.97 m ²) / Carton 8 pieces / Carton 44.25 lbs (20.07 kg) / Carton
Installation Method:	Floating

Testing – NALFA LF-01-2011

3.1 Static Load	≥ 6 MPa (870 psi) [†]
3.2 Thickness Swell	≤ 16%
3.3 Light Resistance	No Effect
3.4 Cleanability / Stain Resistance	Score < 20 No Effect
3.5 Large Ball Impact Resistance	> 1000mm (39.4in)
3.6 Small Ball Impact Resistance	≥ 200mm (7.9in)
3.7 Wear Resistance	IP ≥ 2000 Cycles
3.8 Dimensional Tolerances (Maximum)	Pass
3.9 Castor Chair Resistance	25000 Cycles No Effect

Additional Testing

HUD/FHA	
Flooring Radiant Panel (ASTM E648)	
Smoke Density (ASTM E662) Coefficient of Friction (ASTM D2394) Sound Dissipation	Meets or Exceeds
AC Rating	Passes - Class 1; CRF Value ≥ 0.45 watts/cm ² Passes - ≤ 450
Environmental Data	Meets or Exceeds Passes - STC 54; IIC 59 (Using Mannington Underlayment) Rated AC3

Indoor Air Quality	Low VOC, FloorScore Certified; CDPH V1.2-2017
LEED Scoreboard	May contribute to LEED credits: Building Product Disclosure & Optimization - Sourcing Raw Materials Building Product Disclosure & Optimization - Material Ingredients; IEQc2 - Low Emitting Materials
Manufacturing	High Point, NC

For more information, contact your Mannington on Main representative or visit

ManningtonOnMain.com